



PROTECTIVE GLOVES

made in EU

& developed in EU

AntiCut SMOKE



EN 388:2016+A1:2018

Abrasion resistance	4
Cut resistance Coupe test	X
Tear resistance	4
Puncture resistance	3
Cut resistance TDM	D

EN ISO 13997 is 16,3 N (Newton)

Material: BRINIX® A1SM

Size: 6, 7, 8, 9, 10, 11



AntiCut K 185



EN 388:2016+A1:2018



Abrasion resistance	2
Cut resistance Coupe test	5
Tear resistance	4
Puncture resistance	2
Cut resistance TDM	F

EN ISO 13997 is 36,7 N (Newton)

Material: BRINIX® AK185

Size: 6, 7, 8, 9, 10, 11



AntiCut K 155



EN 388:2016+A1:2018

Abrasion resistance	2
Cut resistance Coupe test	5
Tear resistance	4
Puncture resistance	2
Cut resistance TDM	F

EN ISO 13997 is 36,7 N (Newton)

Material: BRINIX® AK155

Size: 6, 7, 8, 9, 10, 11



AntiCut BAX



EN 388:2016+A1:2018

Abrasion resistance	4
Cut resistance Coupe test	X
Tear resistance	4
Puncture resistance	2
Cut resistance TDM	E

EN ISO 13997 is 24,3 N (Newton)

Material: BRINIX® A1BAX

Size: 6, 7, 8, 9, 10, 11



EN 407:2020

Limited flame spread	X
Contact heat	1
Convective heat	X
Radiant heat	X
Small drops of molten metal	X
Large quantities of molten metal	X



SharpKing SKY STEEL SB



EN 388:2016+A1:2018

Abrasion resistance	3
Cut resistance Coupe test	4
Tear resistance	4
Puncture resistance	3
Cut resistance TDM	F

EN ISO 13997 is 35,4 N (Newton)

Material: BRINIX® SH1SSB

Size: 6, 7, 8, 9, 10, 11



Panzerhand URSUS



EN 388:2016+A1:2018

Abrasion resistance	4
Cut resistance Coupe test	5
Tear resistance	4
Puncture resistance	1
Cut resistance TDM	F

EN ISO 13997 is 96,9 N (Newton)

Material: BRINIX® P1U

Size: 6, 7, 8, 9, 10, 11



EN 407:2020

Limited flame spread	X
Contact heat	1
Convective heat	X
Radiant heat	X
Small drops of molten metal	X
Large quantities of molten metal	X



AntiCut AMX



EN 388:2016+A1:2018

Abrasion resistance	2
Cut resistance Coupe test	5
Tear resistance	4
Puncture resistance	2
Cut resistance TDM	D

EN ISO 13997 is 17,0 N (Newton)

Material: BRINIX® A1A

Size: 6, 7, 8, 9, 10, 11



EN 407:2020

Limited flame spread	X
Contact heat	1
Convective heat	X
Radiant heat	X
Small drops of molten metal	X
Large quantities of molten metal	X



AntiCut SURPRISE



EN 388:2016+A1:2018

Abrasion resistance	X
Cut resistance Coupe test	X
Tear resistance	X
Puncture resistance	X
Cut resistance TDM	D

Material: BRINIX® A1SUR

Size: 6, 7, 8, 9, 10, 11



AntiCut AMX STEEL



EN 388:2016+A1:2018

Abrasion resistance	3
Cut resistance Coupe test	5
Tear resistance	4
Puncture resistance	2
Cut resistance TDM	F

EN ISO 13997 is 43,8 N (Newton)

Material: BRINIX® A1AS

Size: 6, 7, 8, 9, 10, 11



EN 407:2020

Limited flame spread	X
Contact heat	1
Convective heat	X
Radiant heat	X
Small drops of molten metal	X
Large quantities of molten metal	X



AntiCut SHADOW



EN 388:2016+A1:2018

Abrasion resistance	3
Cut resistance Coupe test	5
Tear resistance	4
Puncture resistance	2
Cut resistance TDM	F

EN ISO 13997 is 74,5 N (Newton)

Material: BRINIX® A1SH

Size: 6, 7, 8, 9, 10, 11



EN 407:2004

Limited flame spread	X
Contact heat	1
Convective heat	X
Radiant heat	X
Small drops of molten metal	X
Large quantities of molten metal	X



SharpKing FINE STEEL



EN 388:2016+A1:2018



Abrasion resistance	3
Cut resistance Coupe test	4
Tear resistance	4
Puncture resistance	2
Cut resistance TDM	F

EN ISO 13997 is 63,4 N (Newton)

Material: BRINIX® SH1FS

Size: 6, 7, 8, 9, 10, 11



SharpKing BLUE



EN 388:2016+A1:2018

Abrasion resistance	2
Cut resistance Coupe test	5
Tear resistance	4
Puncture resistance	X
Cut resistance TDM	C

EN ISO 13997 is 10,7 N (Newton)

Material: BRINIX® SH1

Size: 6, 7, 8, 9, 10, 11



EN 407:2004

Limited flame spread	X
Contact heat	1
Convective heat	X
Radiant heat	X
Small drops of molten metal	X
Large quantities of molten metal	X



AntiHeat TOKYO



EN 388:2016+A1:2018

Abrasion resistance	2
Cut resistance Coupe test	4
Tear resistance	4
Puncture resistance	4
Cut resistance TDM	C

EN ISO 13997 is 15,7 N (Newton)

Material: BRINIX® A1TO

Size: 6, 7, 8, 9, 10, 11



EN 407:2020

Limited flame spread	4
Contact heat	3
Convective heat	3
Radiant heat	X
Small drops of molten metal	X
Large quantities of molten metal	X



MIRO REX



EN 388:2016+A1:2018

Abrasion resistance	4
Cut resistance Coupe test	1
Tear resistance	2
Puncture resistance	1
Cut resistance TDM	A

Material: BRINIX® M1REX

Size: 6, 7, 8, 9, 10, 11



CONDUCTIVE



EN 388:2016+A1:2018

Category I.
Minimal risks
Superficial mechanical injury
ESD protection

Material: BRINIX® CON

Size: 6, 7, 8, 9, 10, 11



MIRO GLOVES s.r.o.

Borova 275, 569 82 Borova, Czech Republic, tel.: +420 607 847 847, mail: sales@anticut.com

www.anticut.com



www.gloves.cz